

Sikagard®-207 W (Biosheen)

Single component, waterborne modified acrylic resin surface coating with a mid-sheen finish

Product Description	Sikagard®-207 W is a single component, coloured, waterborne modified acrylic resin based surface coating containing an inorganic in-film preservative.
Uses	<ul style="list-style-type: none">■ Coloured coating for internal walls and ceilings■ For concrete, cement based and gypsum substrates and previously painted surfaces■ Suitable for clean rooms in the pharmaceutical and medical industry. Also suitable for food and beverage industry, hospitals, kitchens and prisons and leisure facilities■ Overall basic hygiene protection for large areas■ General use in domestic situations
Characteristics / Advantages	<ul style="list-style-type: none">■ Easy application■ Fast drying, two coats in one working day■ Elastomeric, resists cracking and flaking■ Good resistance to repeated cleaning regimes using mild detergents and cleaning solutions■ Good water vapour permeability■ Seamless, easy clean mid-sheen finish■ Good covering and hiding power (opacity)■ Low odour
Tests	
USGBC LEED rating	Sikagard®-207 W conforms to the requirements of LEED EQ Credit 4.2: Low –Emitting Materials: Paints & Coatings SCAQMD Method 304-91 VOC Content < 100g/l
Wet-srub resistance	ILF Magdeburg, Test report: 1-034/10 Class 1; acc. EN 13300
Hiding power	ILF Magdeburg, Test report: 1-034/10 Class 1; acc. EN 13300
Antibacterial activity	Hohenstein Laboratories GmbH, Test report: 10.8.3-0058-4 Acc. ISO 22196, 2007 and JIS Z 2801,2000 test report available on request

Construction



Product Data

Form

Appearance / Colour	Resin: Standard colour shade:	Liquid, coloured White, light blue (BS 18E49), sage (BS12B21), magnolia (BS08B15). All colour shades acc. BS 4800 light grey (RAL 7035), pearl white (RAL 1013), cream white (RAL 9001) and grey white (RAL 9002) Special colours may be made to order subject to minimum order quantities.
----------------------------	----------------------------------	---

Packaging	Sikagard®-207 W (Biosheen):	5.0 litres (= 6.55kg) containers 15.0 litres (= 19.65kg) containers
------------------	-----------------------------	--

Storage

Storage Conditions/ Shelf-Life	24 months from date of production if stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5°C and +25°C. Avoid exposure to frost and sources of heat.
---------------------------------------	---

Technical Data

Chemical Base	Waterborne modified acrylic resin	
Density	Sikagard®-207 W (Biosheen):	~ 1.31 (DIN EN ISO 2811-1)
Solid Content	~ 38.2% (by volume) / ~ 52.2% (by weight)	
Adhesion	<i>To concrete:</i> > 1.5 N/mm ² (failure in concrete)	

Mechanical / Physical Properties

Tensile Elongation	Unreinforced:	~30% (BS EN ISO 527-3)
---------------------------	---------------	------------------------

Chemical resistance	10% solutions of acids and alkalis including nitric acid and caustic soda failed to cause breakdown of the membrane
----------------------------	---

Hydrogen Peroxide	Resistant to a disinfection regime, based on H ₂ O ₂ gas exposure up to 5 hours
--------------------------	---

System Information

System Structures	System 1: Good surface of blockwork, brick, stone, calcium silicate board, concrete, high pressure laminate, insulation materials, mastic, moisture resistant plasterboard, plasterboard, sand & cement render, tiles and timber (please refer to Technical Customer Services for further information): Primer: 1 x Sika® Bonding Primer Top coat: 2 x Sikagard®-207 W System 2: Maintenance of good surfaces of blockwork, brick, stone, calcium silicate board, concrete, high pressure laminate, insulation materials, mastic, moisture resistant plasterboard, plasterboard, sand & cement render, tiles and timber (please refer to Technical Customer Services for further information): Primer: 1 x Sika® Bonding Primer Intermediate coat: 1 x Sikagard®-203 W Top coat: 2 x Sikagard®-207 W
--------------------------	--

Application Details

Consumption / Dosage

Coating System	Product	Consumption
System 1		
Primer	1 x Sikagard®-207 W (10% diluted)	Approx. 0.21 kg/m ²
Top coat	2 x Sikagard®-207 W	Approx. 0.21 kg/m ²
System 2		
Primer	1 x Sika® Bonding Primer	Approx. 0.10 kg/m ²
Intermediate coat	1 x Sikagard®-203 W	Approx. 0.35 kg/m ²
Top coat	2 x Sikagard®-207 W	Approx. 0.21 kg/m ² , each coat

Note:

These figures are theoretical and do not allow for any additional material required due to surface porosity, surface profile, variations in level and wastage etc.

Substrate Quality

The substrate must be sound, clean, dry and free of all contaminants such as dirt, laitance, mould, oil, grease and surface treatments, etc.

If in doubt apply a test area first.

Substrate Preparation

All surfaces to be coated should be thoroughly cleaned by conventional means.

Exposed metal surfaces to be included in the coating schedule should be wire brushed or mechanically abraded to remove rust/ scale or oxidation. Return to a clean, bright metal wherever possible.

Ensure that surfaces are free from visible dampness and that all dust, loose and friable material is completely removed from all surfaces before application of the product, preferably by brush and/or vacuum.

Application Conditions / Limitations

Substrate Temperature

+5°C min. / +35°C max.

Ambient Temperature

+5°C min. / +35°C max.

Substrate Moisture Content

Visible damp free (maximum 18% wood moisture equivalent).

< 6% pbw moisture content Test method: Sika®-Tramex meter,
< 4% CM - measurement or Oven-dry-method.

No rising moisture according to ASTM (Polyethylene sheet).

Relative Air Humidity

80% r.h. max.

Dew Point

Beware of condensation!

The substrate and uncured coating must be at least 3°C above dew point to reduce the risk of condensation or blooming on the wall finish.

Application Instructions

Application Method / Tools

Prior to application, confirm substrate moisture content, relative humidity and dew point.

Primer:

Sika® Bonding Primer can be applied by short-piled roller, brush or airless spray. Sikalastic® Metal Primer can be applied by short-piled roller, brush or airless spray.

Intermediate coat:

Sikagard®-203 W can be applied by short pile or sheepskin roller (for embedment coat only), brush or airless spray. Preferred application is by airless spray.

Top Coat:

Sikagard®-207 W can be applied by medium or long pile roller, brush or airless spray (for further information please contact Technical Customer Services).

Cleaning of Tools

Clean all tools and application equipment with water immediately after use. Hardened and/or cured material can only be removed mechanically or with proprietary paint stripper).

Waiting Time / Over coating

Before applying Sikagard®-207 W - on Sikagard®-203 W - allow:

Substrate temperature	Minimum	Maximum
+10°C	~24 hours	7 days.
+20°C	~4 hours	7 days
+30°C	~4 hours	7 days

Before applying Sikagard®-207 W - on Sikagard®-207 W - allow:

Substrate temperature	Minimum	Maximum
+10°C	~4 hours	7 days
+20°C	~1 hours	7 days
+30°C	~1 hours	7 days

Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.

Notes on Application / Limitations

Application by roller may result in a slight surface texture when using standard coverage rates. If a smoother surface is required apply 3 thinner coats to produce the same overall DFT.

Always ensure good ventilation when using Sikagard®-207 W in a confined space, to ensure drying and full curing.

The gloss of the applied material is influenced by humidity, temperature and absorbency of the substrate.

The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking (for further information please contact Technical Customer Services).

For spray application the use of protective health & safety equipment is mandatory!

If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO₂ and H₂O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.

New concrete should be allowed to cure/hydrate for a minimum of 10 days and preferably 28 days.

Curing Details

Applied Product ready for use

Temperature	Tack free	Full cure
+10°C	~ 4 hours	~ 24 hours
+20°C	~ 1 hour	~ 4 hours
+30°C	~ 1 hour	~ 4 hours

Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.



Value Base	All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.
Local Restrictions	Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.
Health and Safety Information	For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.
Legal Notes	The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.
EU Regulation 2004/42	According to the EU-Directive 2004/42, the maximum allowed content of VOC (Product category IIA / j type wb) is 140 / 140 g/l (Limits 2007 / 2010) for the ready to use product.
VOC - Decopaint Directive	The maximum content of Sikagard®-207 W is < 140 g/l VOC for the ready to use product.

Sika Limited
 Watchmead
 Welwyn Garden City
 Hertfordshire
 AL7 1BQ
 United Kingdom
 Phone +44 1707 394444
 Telefax +44 1707 329129
www.sika.co.uk
 email: sales@uk.sika.com



Certificate No. EMS 4308



Certificate No. FM 12504